

SILFIX[®] HM

Version No. 3

Revision Date: 24/04/09

Page 1 of 2

DESCRIPTION

Silfix[®] HM is a premium quality high modulus acetoxycure silicone sealant which offers outstanding strength, performance and durability. It is ideal for use in a wide variety of glazing, industrial and domestic applications and is ideal for use in glass/glass joints, shop fronts, kitchens and bathrooms. Conforms fully to the requirements of ISO 11600 Classification G-25 HM and BS5889 Type B.

KEY FEATURES

Excellent unprimed adhesion to a wide variety of surfaces including glass and glazed surfaces, coated metals and some plastics.

Contains a powerful fungicide (white only) which makes it ideal for use around baths, basins, ceramic tiles etc.

Fast curing acetoxycure system.

Good performance across a wide range of temperatures.

TECHNICAL APPROVALS

Silfix[®] HM conforms to the following standards: ISO 11600 Classification G-25 HM and BS 5889:1989 Type B

USES

For sealing joints between Plastisol and alkyd coated steel.
Trims and flashing in roofing and cladding.
PVC-U, aluminium, steel, timber frame/door surrounds.
Wall tiling.
Many forms of expansion/construction joints in building superstructures.

Glass to glass joints such as shop fronts where a high structural strength is required.
General industrial use eg heating & ventilation, sectional buildings, caravans etc.
For sealing joints in glass aquaria. **Only Silfix HM Translucent is suitable for sealing joints in glass aquaria.**

Note: Do not use in contact with edge sealants of double glazed units or where it will be in contact with lead, brass and copper.

PERFORMANCE

Adhesion: Excellent to glass and glazed surfaces, coated metals, painted timber and some plastics. For further details contact our Technical Department.

Base technology: Silicone polymer

Chemical resistance: Excellent to dilute acids and alkalis

Curing system: Acetoxycure

Hardness (Shore A 25°C): 25-35

ISO 11600 classification: G-25 HM

Mould resistance: Only white contains a fungicide.

Movement accommodation: ±25%

Paintability: Not recommended

Service life (predicted): 20+ years

Service temperature range: -60°C to +200°C

Shrinkage: < 5%

Slump: Nil

Specific gravity: 1.02g/cm³ translucent, 1.04g/cm³ colours

Staining: Nil on most surfaces

Tensile strength: >0.6 N/mm²

UV resistance: Excellent

Volatile content: < 5%

PRODUCT DATA SHEET



SILFIX® HM

Version No. 3

Revision Date: 29/04/09

Page 2 of 2

APPLICATION

PROPERTIES

Application temperature range: +5°C to +30°C

Curing rate: Cures at a rate of 3mm in 24 hours at 23°C @ 60% RH. Lower temperatures and drier conditions will result in a slower rate of cure.

Shelf life: 18 months.

Skinning time: skin forms after approximately 30 minutes at 23°C @ 60% RH.

Working time: Approximately 10 minutes depending on conditions.

INSTRUCTIONS

Joint design: Please consult the **Technical Information Sheet** entitled 'Joint design for cartridge based products' prior to application.

Surface preparation: All surfaces must be clean, dry and free from frost, grease and loose materials. Apply primer if required. In situations where an especially neat finish is required, use masking tape to cover the face edges of the joint and remove immediately once tooling has been completed.

Cut the tip of the screw thread off the cartridge and screw on the nozzle. Cut nozzle to correct diameter for joint size. Apply using a skeleton or powered gun into the joint ensuring good contact with surfaces. In deep joints, the use of Hodgson Backing Rod is essential to ensure good joint formation.

Tooling: Tool immediately after sealant has been applied within the working time for the product.

EQUIPMENT

A selection of hand & air operated guns is available for cartridge application including a high power type especially suitable for filling deep voids.

PACKAGING

310ml cartridges – 25 per carton

Standard Colours: White, translucent, black, brown

ESTIMATING QUANTITIES

$$\text{Number of cartridges} = \frac{\text{Joint depth (mm)} \times \text{Joint width (mm)} \times \text{Length (M)}}{\text{Volume of cartridge (ml)}}$$

This calculation does not allow for wastage.

HEALTH AND SAFETY

Use only in well-ventilated areas. Avoid contact with skin.

Wash hands immediately after use. See Product Safety Data Sheet for further information.

GENERAL

Silfix® HM is part of a full range of speciality sealants and tapes designed for the professional user. For further information please contact our Customer Care Team or visit our Website.

The information given in this product data sheet is based on laboratory tests and experience which we believe to be correct. Properties quoted are typical and do not therefore constitute a specification. In view of the wide range and variability of substrates, we would advise that our product should be tested by the user to establish suitability for its intended application. E & OE.

Hodgson Sealants Limited

Belprin Road, Beverley, East Yorkshire,
HU17 0LN, United Kingdom

T: +44 (0)1482 868321

F: +44 (0)1482 870729

W: www.hodgsonsealants.com

E: sales@hodgsonsealants.com

Registered in England No. 2799221 | Registered Office. Belprin Road, Beverley, East Yorkshire, HU17 0LN, United Kingdom | VAT REG. No. GB 856 3436 07